



Pineapple Sails
2526 Blanding Ave.
Alameda, CA. 94501
510-522-2200
www.pineapplesails.com
Source: Glen Raven Mills

REDUCE ENERGY COSTS

Solar protection properties of Sunbrella awning fabrics

46" (116.8 CM)	NAME	LIGHT TRANSMITTANCE TOTAL, TV (%)	SOLAR TRANSMITTANCE TOTAL, TS (%)	UV TRANSMITTANCE TOTAL, TUV (%)	46" (116.8 CM)	NAME	LIGHT TRANSMITTANCE TOTAL, TV (%)	SOLAR TRANSMITTANCE TOTAL, TS (%)	UV TRANSMITTANCE TOTAL, TUV (%)	46" (116.8 CM)	NAME	LIGHT TRANSMITTANCE TOTAL, TV (%)	SOLAR TRANSMITTANCE TOTAL, TS (%)	UV TRANSMITTANCE TOTAL, TUV (%)
4600	ERIN GREEN	0.1	0.6	0.0	4626	NAVY	0.0	0.0	0.0	4658	BRASS	1.4	3.7	0.2
4601	PACIFIC BLUE	0.1	7.4	0.0	4628	TOAST	1.6	11.8	0.2	4665	CONCORD	0.0	8.5	0.0
4602	SUNFLOWER YELLOW	12.5	18.3	0.0	4630	CADET GREY	1.5	11.9	0.6	4666	LOGO RED	0.9	12.3	0.1
4603	JOCKEY RED	0.3	11.7	0.0	4631	BURGUNDY	0.0	7.3	0.0	4667	MAHOGANY	0.0	0.0	0.0
4604	NATURAL	23.9	24.1	10.8	4632	IVY	0.0	0.9	0.0	4668	ASPEN	1.1	11.8	0.2
4605	HEMLOCK TWEED	0.0	0.1	0.0	4633	LINEN	4.4	13.4	1.2	4671	FERN	0.0	0.1	0.0
4606	DUBONNET TWEED	0.0	0.9	0.0	4635	BUTTERCUP	15.7	18.8	0.2	4672	HEATHER BEIGE	0.8	3.6	0.1
4607	CHARCOAL TWEED	0.3	1.3	0.2	4637	FOREST GREEN	0.0	0.0	0.0	4673	SPA	1.0	8.5	0.1
4608	BLACK	0.0	0.0	0.0	4640	BLACK CHERRY	0.0	0.0	0.0	4674	WHEAT	3.1	13.1	0.3
4609	ORANGE	3.8	15.6	0.8	4641	SAPPHIRE BLUE	0.0	1.2	0.0	4675	CAPRI	0.4	9.9	0.1
4610	TURQUOISE	0.1	2.2	0.0	4642	OYSTER	16.1	19.9	7.0	4676	COCOA	0.0	8.0	0.0
4614	TAN	0.1	0.3	0.0	4643	PERSIAN GREEN	0.1	4.2	0.0	4677	TUSCAN	1.4	13.0	0.0
4616	MOCHA	3.5	4.2	1.4	4644	CHARCOAL GREY	0.0	0.1	0.0	4678	MARINE BLUE	0.0	0.0	0.0
4617	ROYAL BLUE	0.0	1.8	0.0	4645	SEAGRASS GREEN	0.1	4.7	0.0	4679	OCEAN BLUE	0.0	7.3	0.0
4618	WALNUT BROWN TWEED	0.0	0.0	0.0	4646	CAPTAIN NAVY	0.0	0.0	0.0	4683	PARCHMENT	15.6	19.7	3.8
4620	BEIGE	0.3	1.2	0.0	4648	TAUPE	0.1	0.4	0.0	4684	SLATE	0.0	0.0	0.0
4621	TRUE BROWN	0.0	0.0	0.0	4651	SILVER	12.5	17.9	5.8	4685	GINKGO	1.0	6.4	0.0
4622	TERRACOTTA	0.0	0.3	0.0	4652	MEDITERRANEAN BLUE	0.0	7.3	0.0	4686	NUTMEG	0.1	1.9	0.0
4623	AQUAMARINE	0.5	2.3	0.0	4653	MED. BLUE TWEED	0.0	2.2	0.0	4688	BASIL	0.6	9.5	0.1
4624	SKY BLUE	1.0	6.0	0.2	4654	LINEN TWEED	1.4	3.7	0.4	4689	RUST	0.2	2.5	0.0

LABORATORY METHOD: EN 410:1998 THE OPENNESS FACTOR FOR ALL FABRICS IS LESS THAN 0.1 %.